

# ROBERTSON & STEWART, INC.

1351 RICKETT ROAD  
BRIGHTON, MICH. 48116  
Phone (313) 227-4500  
Duns 07-637-5005

May 12, 1987

1010 Steel

Four samples identified as A, B, C1, C2 were received from Dynamic Metal Treating and were subjected to 168 hours salt spray as per ASTM-B-117 with results as follows:


Sample A - Nitrowear Plus - less than 2% red rust.

Sample B - Nitrowear - less than 2% red rust.

Sample C1 - Nitrowear - No red rust.

Sample C2 - Nitrowear - No red rust.

\*\*\*NOTE - All four samples passed the 168 hour salt spray requirement.

  
ROBERTSON & STEWART, INC.