

**MIDWEST TESTING LABORATORIES, INC.**

1072 WHEATON • PHONE (248) 689-9262 • TROY, MICHIGAN 48083

FAX (248) 689-7637

ORIGINAL REPORT OF ANALYSIS

DYNAMIC METAL TREATING #713
7784 RONDA DRIVE
CANTON TWP., MI 48187

MTL#3L772 (PG. 1 OF 1)
DATE RECEIVED: 8/4/98
DATE COMPLETED: 8/24/98
BY: ED LESTERSON
P.O. # 2132

SAMPLE OF. 6 pc.
SAMPLE NO. OR DESCRIPTION:

SPECIFICATION REQUIRED: B117

SALT SPRAY:

Six (6) samples tested were subjected to 126 hour neutral salt spray testing per ASTM B117.

Dyna Blue - 3 pieces 5% base metal corrosion
1 piece > 10% base metal corrosion

409 Stainless -1 piece 5% base metal corrosion
1 piece > 10% base metal corrosion

*Sample returned to Dynamic Metal Treating, Inc for evaluation.

THIS DOCUMENT CAN ONLY BE REPRODUCED IN FULL.

We certify the above analysis to be the true results on the designated samples.

MIDWEST TESTING LABORATORIES, INC.

Raymond D. Westbrook
Director of Laboratory

ID# 100258 EXPIRATION 01/2000

